

KIMIYA TEJARAT

PARTAK Co.

Trading Company

LOMON TiO₂ R-996

Technical index - R-996

TYPICAL PROPERTIES		
Parameter	Value	Test Method
TiO ₂ content	95%	XRF
Inorganic coating	Alumina; Zirconia	—
Organic treatment	Present	—
Moisture when packed*	0.5% max	ISO 787-2
Bulk density (tamped)	1.2g/cm ³	ISO 787-11
Oil absorption	18g/ 100g	ISO 787-5
pH	7.0	ISO 787-9
Specific gravity	4.1g/cm ³	ISO 787-10
Specific gravity	R2	—
CAS number	13463-67-7	—
Color index	Pigment White 6	—

Careful control of the TiO₂ particle size during the manufacturing process of BILLIONS™ R-996 pigment results in good brightness, high opacity and easy dispersibility.

TITANIUM DIOXIDE

R-996



Addresses:

No. 908, 9th Floor, Alvand tower, Ebrahimi St, Marzdaran, Tehran, Iran

Phone: +98 21 44 22 57 61 / +98 21 44 22 57 49

Cellphone: +98 912 044 2834

Web: kt-partak.ir

Email: info@kt-partak.ir